



Compressive Strength Evaluation of M20 Grade Concrete by Using Cowdung

Tanveer Asif Zardi	Director, Professor Head of Civil Department KCT Engineering college, C/o Dr Meenaz Hospital H No 5-408/40/1&2, Near KBN Inst of Medical Sciences Madeena colony, Gulbarga Karnataka
Mohammed Fariduddin	UG Student, Department Of Civil Engineering, V.T.U University K.C.T.E.C, Gulbarga, Karnataka
Mohammed Jaleel	UG Student, Department Of Civil Engineering, V.T.U University K.C.T.E.C, Gulbarga, Karnataka
Md Yousuf	UG Student, Department Of Civil Engineering, V.T.U University K.C.T.E.C, Gulbarga, Karnataka

ABSTRACT

This research aims to find out the optimum compressive strength of concrete produced with partial replacement of cement with cow dung and fine aggregates with sawdust. The concrete mix of 1:1.5:3 was prepared using water/cement ratio of 0.65 with 0%, 2%, 4% and 6% cow dung and 6% sawdust were used concurrently as partial replacement for fine aggregates and cement respectively. It was also discovered that as curing age increases, the compressive strength increases and increase in percentage replacement caused a corresponding decrease in the compressive strength. The Compressive strength value obtained were found to conform to the minimum requirement of 20N/mm² for light weight concrete especially when 2% fine aggregate were replaced with cow dung and sawdust respectively.

KEYWORDS : Optimum Compressive Strength, Curing, Water/Cement Ratio, Saw Dust, Cow dung.

I. INTRODUCTION

The cost of building construction is increasing daily as a result of increasing in the cost of building materials such as cement, granite, fine aggregates etc. This has prevented the low income earners to have their own house. Also, the agricultural and industrial wastes pose great hazard to environment and man as a result of improper management even when these wastes are burnt, they release carbon-monoxide to atmosphere which depletes the ozone layer. If these wastes are processed, they may be suitable for construction purpose. Concrete is a mixture of cement, fine aggregates, coarse aggregates and water in a right proportion to get a particular strength. The paste formed as a result of reaction between water and cement binds the aggregates together. The mixture sets into a rock-like solid mass, which has considerable compressive strength but little resistance in tension.

However, the construction industry relies heavily on conventional materials such as cement, granite, and for production of concrete in some areas, the demand for these conventional materials is higher than supply and this has hindered the development of shelter and other infrastructural facilities in such areas. The growing concern of resource depletion and global pollution has challenged many researchers and Engineers to seek and develop locally available materials to suit engineering purpose.

II. SCOPE AND OBJECTIVE:

The purpose of the present dissertation work is summarized as the following objectives:

To evaluate performance of light weight concrete.

To evaluate several laboratory specimen.

To make concrete production as cost effective.

The implementation of waste sawdust can not only decrease environmental damage, but also can save the concrete materials.

It has many advantages over traditional concrete, such as low bulk density, better heat preservation and heat insulation property.

It has lower pollution for our environmental impact. It is also eco-friendly.

A paradigmatic use of waste sawdust and cow dung.

III. MATERIALS AND METHODS

Cow dung: This is obtained from the cow excreta. It was sundried and grounded to fine powder form like cement. The grounded cow dung particles were sieved through 90microns and used for concrete production without further treatment.

The percentage replacements for cement were varied from 0%, 2%, 4% and 6%. The cow dung was obtained.

Sawdust: It was obtained from saw mill industry and sieved and retained on sieve aperture of 600microns, sundried, then kept in water-proof bags and used without further treatment. The percentages of replacements of fine aggregates by sawdust were 6%.

Cement: Portland cement was used for this research work and it was found to conform with the requirements of IS 10262:2009

Water: The water used for this work is potable, clean and free from any visible impurities. It confirmed to IS 10262:(2009).

Fine aggregates: The fine aggregates used for this work is stone dust. It was retained on a 600microns sieve. The impurities were removed and found confirmed to the requirements of IS 10262: (2009).

Coarse aggregates: Granites were used for this work of size 12.5mm. They are free from debris and other impurities. They are angular in shape. The tests carried out on these materials are slump test, sieve analysis, specific gravity and compressive strength

Slump test: The most widely used test for determine the workability of concrete. The test is a measure of the resistance of concrete to flow under its weight. The apparatus used is a hallow cone shaped mould test.

Compressive strength test: The compressive strength of concrete is one of the most important and useful properties of concrete. The primary purpose for design concrete is to resist compressive strength in structural members.

Hence it is the role of a concrete designer to specify the expected characteristics strength of concrete/mix proportion to enable it resist external force.

Sieve analysis: This is a test that is performed to determine the percentage of different grain sizes contain within the material.

The mechanical sieve analysis is performed to determine the distribution of coarser, larger-sized particles. The sieve analysis of this study was carried out on saw dust.

Specific gravity test: This is a test that is performed to determine the density of the soil particle finer than 2mm. At least two specimens, each between 5g and 10g shall be obtained by riffing. The specimens shall be oven dried or sundried at 1050c to 1100c and stored in an airtight container.

Table -1 physical properties of material

Material	Specific gravity	Water absorption	Fineness modulus
Cement	3.13	--	<100 micron
Fine aggregate	3.00	1%	4.84
Saw dust and cow dung	1.25 and 1.33	0.20%	>600 micron
Coarse aggregate	2.72	0.5%	2.82

IV. EXPERIMENTAL PROGRAM

The saw dust and cow dung were collected from saw mills and its properties were tested. Analysis was carried out in Concrete mixtures. The concrete mix of 1:1.5:3 was prepared using water/cement ratio of 0.65 with 0%, 2%, 4% and 6%.cow dung and 6% sawdust were used concurrently as partial replacement for fine aggregates and cement respectively. The specific gravity values of cement. The specimens were cast and tested to study the possibility of using saw dust and cow dung as a substitute material for sand in concrete. The control mix, Utilizing SD (Saw dust) and cow dung replaced as the fine aggregate, was designed for the cube. Based on the laboratory trials, the mix proportion of the control mix (M20) was finalized and they were investigated to determine the effect on compressive strength in cubes. The mixture were 0%, 2%, 4%, 6%, with different cow dung value and saw dust 6% sawdust replacement in fine aggregate in analyzed. Tests to determine specific gravity, moisture content , water absorption, Bulk density, Compressive strength of cubes for compressive strength tests 150 x 150 mm cubes. A total of 48 specimens were cast and cured in water at room temperature in the laboratory for 3days 7 .14, .28 days. At the end of each curing period, three specimens for each mixture were tested for Compressive strength was recorded

Table-2 mix proportion

Particulars	plain concrete mix	2%	4%	6%
Cement kg/m3	335.5	335.5	335.5	335.5
Sand kg/m3	800.5	783.5	768.5	752.5
Saw dust cow dung kg/m3	0	16.00	32.00	48.00
Coarse agg kg/m3	1643.35	1643.35	1643.35	1643.35
Water kg/m3	146.74	146.74	146.74	146.74

V. RESULTS AND DISCUSSION

From the analysis done on the compressive strength of M20 concrete using 0%,2%,4% and 6% replacement of cement and fine aggregate with cow dung and saw dust respectively. It was observed that the

compressive strength of concrete at 0% replacement of cement and fine aggregate with cow dung and saw dust was 24.2 N/mm² after curing for 28 days, while the compressive strength of the concrete at 2% replacement of cement and fine aggregate with cow dung and saw dust was 19.9 N/mm² after curing for 28 days as shown on table 1.2 and 1.3.It was also observed that the compressive strength of the concrete at 4% replacement of cement and fine aggregate with cow dung and saw dust was 18.78 N/mm² after curing for 28 days, while the compressive strength of concrete of the concrete at 6% replacement of cement and fine aggregate with cow dung and saw dust was 17.62 N/mm² after curing for 28.

Table-3 Specific gravity test for different materials

Materials	Specific gravity
Cow dung	1.33
Stone dust	3.0
Saw dust	1.25
Cement	3.13

Table-4 Compressive strength at different curing age

Percentage replacement	3 days	7 days	14 days	28 days
0	10.2	15.24	21.10	24.2
2	3.90	12.80	17.72	21.3
4	3.78	12.20	16.88	18.78
6	3.20	11.56	16.0	17.62

VI. CONCLUSION

From the computed results and charts obtained from the study (test), it is obvious that the compressive strength of M20 concrete increases with increase in curing days. Also, the compressive strength of concrete at 0% replacement of cement and fine aggregate with cow dung and saw dust is greater than the compressive strength of concrete at 2% replacement of cement and fine aggregate, while the compressive strength of concrete at 2% replacement of cement and fine aggregate with cow dung and saw dust is also greater than the compressive strength of concrete at 4% replacement of cement and fine aggregate with cow dung and saw dust. The compressive strength of concrete at 4% replacement of cement and fine aggregate with cow dung and saw dust was greater than the compressive strength of concrete at 6% replacement of cement and fine aggregate with cow dung and saw dust. In other words, the compressive strength of concrete reduces with increase in the percentage of replacement of cement and fine aggregate with cow dung and saw dust (i.e. the higher the percentage of replacement of cement and fine aggregate with cow dung and saw dust the lower the compressive strength of the concrete).

REFERENCES

- [1] A. A. Raheem 2013 Saw Dust Ash as Partial Replacement for Cement in Concrete ISSN: 2248-9622
- [2] Ayeni October [2015] Investigation of Properties of Concrete Using Sawdust as Partial Replacement for Sand ISSN: 2278-800X
- [3] Divakar,Y Manjunath S. & Aswath M. U. (2012) Experimental Investigation on Behavior of Concrete with the Use of Granite Fines. International Journal of Advance Engineering Research. ISSN: 2278-0181
- [4] Dr. P. Sri Chandana Experimental Study on Strength of Concrete by Partial Replacement of Fine Aggregate with Sawdust. ISSN No: 2348-4845
- [5] Elinwa A. U. & Abdulkadir S. (2011) Charactering Saw dust Ash for Use as an Inhibitor for Reinforcement. ISSN No: 2348-4845
- [6] Lea FM (1988) The chemistry of cement and concrete, Arnold Ltd, London.ISSN 1819-6608
- [7] Olugbenga Joseph Oyedepo Investigation of Properties of Concrete Using Sawdust as Partial Replacement for Sand ISSN 2224-5790
- [8] Tomas U. Ganiron , (2014) Effect of Sawdust as Fine Aggregate in Concrete Mixture for Building Construction) ISSN 2225-0514