

K. KemparajuFaculty of Biochemistry, University of Mysore, Mysuru, Karnataka.K. Thyaga Raju*Department of Biochemistry, Sri Venkateswara University, Tirupathi-517 502 Andhra
Pradesh. *Corresponding Author

ABSTRACT The Silver nanoparticles (Ag Np) are widely used in topical dressings for treatment of infection during burns, open wounds, and chronic ulcers. In the present study a medicinal plant ie, Trichodesma indicum which cures many diseases was selected for its snake antivenom activity with the combination of silver along with plant extract. The silver and plant extract mixture prepared was said to be Trichodesma indicum silver nanoparticles (TiAgNps). These prepared TiAgNPs were characterized by using UV-Vis spectroscopy, DLS, SEM and FTIR. These nanoparticles on UV absorption showed λ maximum at 440nm, the chemical analysis using FTIR has revealed the presence of Phenols, aromatics, aliphatic amines, carboxyl amines, amides and polyphenols, the SEM analysis showed the appearance spherical, triangular and cuboidal structures on 20, 10, and 2µm spaces, the density light scattering analysis further revealed that it exists as colloidal particle with the size of 87.2nm and with zeta potential of -32.6mV. Having of these properties the leaf extract particles found to inhibit enzymes of Russell viper (Daboia russelli) venom at 10µg/ml. However the fluorescent microscopy analysis of these two has revealed that the stem AgNps on comparison to leaf AgNps the formation of cell clumps were even not found. Therefore AgNps at 10µg/ml having various shapes and sizes inhibit the venom activities of Russell viper in blood systems. The In vitro antivenom activity studied was proved that the T.indicum AgNps can serve as alternative for antivenom activity of Russell viper.

KEYWORDS : Nanoparticles, SEM, FTIR, Russell viper and venom neutralization.

INTRODUCTION

Silver nanoparticles (AgNps) are increasingly used in various fields, including medical, food, health care, consumer, and industrial purposes, due to their unique physical and chemical properties. These include optical, electrical, thermal, high electrical conductivity, and biological properties (Gurunathan *et al* 2015; Li *et al* 2010; Mukherjee *et al* 2001). Many reports were documented on the biogenesis of silver nanoparticles using several plant extracts (Suman *et al* 2018, Vanaja *et al* 2014). The unique activities of physical and chemical properties of silver nanoparticles make excellent activities, such as antimicrobial, antivenomic and anti-inflammatory properties for many purposes in the medical field (Suman et al., 2018).

Medicinal plants used to play important role in the development of an impressive number of novel synthetic drugs. Traditional healers are using herbal medications since years to treat snake bites and several other diseases. Natural inhibitors of snake venoms play a significant role in the ability to neutralize the degradation effects induced by venom toxins (Kadali and Kindangi, 2015). Snake bites constitute a health problem in many tropical and sub tropical countries with an estimate of 2.5 million people envenomed each year worldwide. In India alone, 35,000-50,000 deaths were reported every year (Gutierrez et al 2010 and Mohapatra et al 2011). The major families of snakes in India are Elapidae, Viperidae and Hydrophidae (Shaw, George and Nodder, 1797). The most common poisonous snakes in the country are cobra (Naja naja), krait (Bungarus caeruleus), Russell's viper (Daboia russelli) and saw-scaled viper (Echiscarinatus) (Bhavya et al 2014). Among all enzymes present in the snake venom, proteases, phospholipases, and hyaluronidases are reported to be medically important in developing effective antidotes (Santhosh et al 2013). In this perspective, several attempts have been made to develop snake venom antagonists from plants. In folk medicine, plant drug recipes are passed on to generations by oral tradition and are used as antidotes (Alam et al 2003).

In our study we had selected one of the medicinal plants ie, *Trichodesma indicum* R. Br. belongs to the family *Boraginaceae*. It is commonly known as Adhapushpi. This is a perennial medicinal herb distributed in tropical and subtropical Asia, Africa and Australia. In India, it is available on roadsides and stony dry wastelands. In Indian traditional medicine the *Trichodesma indicum* is acrid and bitter tasting, and considered to be thermogenic, emollient, alexteric,

anodyne, anti-inflammatory, carminative, constipating, diuretic, depurative, ophthalmic, febrifuge and pectoral. The whole plant traditionally used as a carminative, laxative, diuretic, depurative and febrifuge. Flowers are sudorific and pectoral, and Leaves depurative. The roots, leaves and flowers are used for medicinal purposes. Leaves and flowers are edible (Ram Krishna and Chattrerjee 2016). The whole plant have antitussive activity (Srikanth et al 2002), anti diarrheal (Perianayagam et al 2005) and anti-inflammatory properties (Perianayagam et al 2006), insecticidal, metal chelating (Anusha et al 2014)and corrosive inhibitor (Alarmal Mangai 2013) Insecticidal activity (Khan et al 2008) and as veterinary medicine. It is a multidrug plant used to reduce or cure inflammation, pain, osteoarthritis and conjuctivitis. The plant is used for expulsion of dead fetus abortion, inhibition of diarrhoea, reduction of sulfur dioxide-induced cough reflex and also to treat breast cancer(Verma et al 2010). The leaves of this plant are used to treat cancer (Ali 2008). The leaves and roots of Trichodesma indicum are effective against snake bites, urinary diseases and used as diuretic. The leaf paste of T. indicum is used to treat stomach disorders, and intestinal worms in cattle, the treatment of mastitis and for uterine prolapsed (Vanitha et al 2015). Roots are made into paste with water and applied externally to swollen joints, inflammations and skin injuries, for diarrhea, dysentery, cough, cold and fever in folk medicine (Periyanayagam et al 2012).

The present work was aimed to isolate the compounds of *Trichodesma indica* to synthesize silver nanoparticles, characterize their structures, and study antivenomic activity of silver nanoparticles (TIAgNps) using various methods on Russell viper venom.

MATERIALS AND METHODS: Procurement Of Chemicals:

All the chemicals used in the present study were of Analytical Grade (AR) and were obtained from Sigma (St. Louis, MO, USA), Fischer (Pittsburg, PA, USA), Merck (Mumbai, India), Ranbaxy (New Delhi, India), and Qualigens (Mumbai, India) scientific companies.

Collection, Preparation and AgNP synthesis:

The Indian medicinal plant, *Trichodesma indicum*, was collected from Sri Venkateswara University campus Tirupathi, Andhra Pradesh, India. Fresh and healthy plants were collected and rinsed with tap water followed by distilled water to remove all the dust and unwanted visible particles. Each part of the plant were separated, like, stem, root,

venom in absence of plant extract served as control.

flower etc and were cut into small pieces and shade dried at room temperature. About 10gms of each of these finely incised leaves and stems of *Tricodesma indicum* were weighed separately and transferred into beakers containing 1000 mL of distilled water, and boiled for about 20 min. The extracts were then filtered thrice through Whatman No. 1 filter paper to remove particulate matter and collected clear solutions of them, and then refrigerated $(4^{\circ}C)$ for further experimentation.

In the typical synthesis of silver nanoparticles, 100mL of leaf and stem extracts, separately, were treated with 900mL of 1mM silver nitrate solution and stored at room temperature after vigorous mixing. The reactions were carried out in darkness (to avoid photoactivation of AgNO₃). Subsequently the synthesis of silver nanoparticles was initially identified by brown colour formation and further monitored by measuring UV-Vis spectra of the reaction mixture (Vanaja *et al* 2014).

UV-Visible Spectroscopy:

The reaction mixture of leaf and stem were subjected to UV-Vis Spectrophotometric measurements to ascertain molecules that absorb ultraviolet or visible light. Formation of silver nanoparticles was detected by spectroscopy because the colored particle solutions showed a peak at 440nm.

Fourier Transform Infrared Spectroscopy (FTIR) Analysis:

Analysis of FTIR to the dried Ag Nps was carried out through the potassium bromide (KBr) pellet (FTIR grade) method in 1:100 dilution ratio and spectrum was recorded in range from 3500-1000cm⁻¹. This analyte was used for the study of functional groups which were present in the sample mixture.

Scanning Electron Microscope (SEM):

Standard protocols were employed for the preparation of *Trichodesma indicum* AgNp and were subjected to the structure determination of nano particle using SEM.

Dynamic Light Scattering (DLS):

Physicochemical characterization of prepared nanomaterials is an important factor for the analysis of biological activities using radiation scattering techniques such as Particle size and Zeta potential of AgNps. The particle size of the synthesized AgNps was detected using intensity and laser diffraction which are poly-dispersed in mixture solution. The stability was further confirmed by Zeta potential of the particles.

Collection of Venom

Lyophilized snake venom of Russell's viper (*Daboia russelli*) was of gift from Prof. K. Kemparaju, Department of Biochemistry, University of Mysore, Manasagangotri, Mysuru.

Preparation Of RBC Cells From Human Blood:

Human blood was collected in glass tubes containing citrate as anticoagulant. The blood samples were centrifuged at 800rpm for 10mins and plasma was carefully removed. The pellet of red blood cells were washed thrice using PBS buffer (0.15MNaCl,10mM phosphate buffer pH 7.0) and then suspended in a fresh PBS buffer at a density of $1.2 \times 10^{\circ}$ cells/mL monitored by a Neubauer chamber. To this 1% of egg albumin was added (Habermann and Neumann 1954; Gutierrez *et al*, 1988) and the resultant mixture was considered as substrate to snake venom PLA,s in the haemolytic assay.

Blood Agar Diffusion Method:

Petri plates and other requirements were wrapped in paper and autoclaved before the experiment. Nutrient agar was prepared and blood was added to the nutrient agar after autoclaving and cooling it to 45°C, and poured in to the plates in laminar air flow and allowed to solidify. After solidification, wells were made by using sterilized glass tube. The wells were loaded with the venom separately in one plate, PBS as control in one plate, plant extracts of leaf and stem on each plate to observe protective action against venom and plant extract, venom in one plate. The zones formed after 24hrs were measured for each plate and recorded.

Phospholipase (PLA₂) Inhibition

Inhibition of PLA₂ was evaluated using egg yolk as substrate in 1% agarose plates according to the method described by Gutierrez *et al* 1988. The PLA₂ inhibition was calculated by measuring the zone of clearance in the presence and absence of plant extract. PLA₂ activity of

Hemolytic Activity:

The venom was preincubated with various concentrations of extracts for 1hour at 37°C. Hemolytic inhibition was determined as Boman and Kaletta, 1957, with slight modifications of Gopi *et al* 2016.

RESULTAND DISCUSSION

UV-Spectroscopy analysis

UV-Vis Spectroscopy is useful and reliable technique for the primary characterization of AgNps in simple, fast, sensitive, and selective mode for different types of colloidal NPs, Formation of silver nanoparticles was detected by using spectroscopy because the colored nanoparticle solution on light absorption showed a peak in between 400-450 nmhowever the maximum light absorption of AgNPs were found at λ 440nm.

Fourier Transform Infra Red (FTIR) Analysis Of Biosynthesized AgNps Using Leaf Extract Of *T.indicum*

The use of FTIR spectrum has become a versatile tool for analysis of plant products in the fields of biochemistry, molecular biology (Schwinte *et al* 2008), ecology (Lang *et al* 2009), physiology (Oliveira *et al* 2008) and agriculture (Artz *et al* 2008). The leaves and stem of *T.indicum* FTIR analysis results have proved that they consists of aromatic compounds, aliphatic amines, carboxyl groups, amide bonds of proteins, polyphenolics, alcohols and phenols.

From the results of **Figure 1 and Table 1** on FTIR analysis of TIAgNps showed peaks at 536, 672, 1352, 1433, 1482, 1630, 2106, 2353 and 3326 cm⁻¹. The peaks at 536 and 672 cm⁻¹ were due to C-H bond aromatic compounds (Litvin *et al* 2013), the peak at 1352 cm⁻¹ was corresponding to C-N stretching vibrations of aliphatic amines (Sanghi and Verma 2009), the peak at 1433 cm⁻¹ was corresponding to C-O stretch of carboxyl groups, the peak at 1482 cm⁻¹ was due to amide band of proteins (Kora *et al* 2012), the peak at 1,630 cm⁻¹ was corresponding to the N-H bend of primary amines, the peak at 2106 cm⁻¹ was assigned to C-O group of polyphenolics, the peak at 2353 cm⁻¹ was corresponding to C-O stretch vibrations of proteins (Ashok *et al* 2010), and the peak at 3,326 cm⁻¹ was related to stretching vibrations of O-H bonds of alcohols or phenols (Thirunavoukkarasu *et al* 2013).




Fig: 1 FTIR chromatogram for leaf AgNps of T.indicum

Table.1	FTIR	Spectral	Peaks	Of	T.indicum	Leaf	Nanoparticles
With Tl	neir Re	spective F	unctio	nal N	Aolecules		

Frequency cm ⁻¹	Bonds	Functional groups					
536, 672	C-H bond	aromatic compounds					
1352	C-N stretching	aliphatic amines					
1433	C-O stretching	carboxyl groups					
1482		amide band					
1630	N-H bend	amines					
2353	C-O stretching	proteins					
3326	O-H bonds	alcohols or phenols					

The FTIR analysis has revealed that the TIAgNps composed of aromatic and aliphatic molecules with the functional groups of hydroxyl, peptides, carboxyl, carbonyl and amines.

Scanning Electron Microscope (SEM):

The field of nanoscience and nanotechnology are provided with a driving force in the development of high-resolution microscopy techniques in order to know more about nanomaterials using a beam of highly energetic electrons to probe objects on a nano scale. Among various electron microscopy techniques, SEM is a surface imaging method, fully capable in resolving different particle sizes, size distributions, nano material shapes, and particle surface morphology of synthesized particles at the micro and nano scales. The results of SEM on synthesized silver nanoparticles of plant were shown in Figure

INDIAN JOURNAL OF APPLIED RESEARCH 81

2. As shown in Figure (3), the SEM analysis has confirmed that the size range of particle was 22 - 40nm, a clear indication of the formation of silver nanoparticles with the beam waves of 20μ m (3A), 10μ m (3B), and 2μ m (3C). The AgNps formed had spherical, triangular and cubic structures. This may be due to availability of different quantity and nature of capping agents. The sizes shapes and radius were supported by the shifts and difference in areas of the peaks obtained on FTIR analysis.




Fig 2: Scaning Electron Microscopy *T.indicum* Leaf Images Of Silver Nanoparticles.

The Dynamic Light Scattering Particle size and Zeta potential analysis of the biosynthesized AgNps of leaf extract of *T.indicum*

Dynamic light scattering (DLS) is a method that depends on the interaction of light with particles when scattered from a laser beam that passed through a colloid solution and used to determine particle size and size distributions in aqueous or physiological solutions (Murdock *et al* 2008; Fissan *et al* 2014). The particle size of the leaf AgNps was detected by (DLS) technique found to be polydispersed with the sizes of 40-100 nm and the average size or hydrodynamic radius of AgNps was found to be 87.2nm (Figure 3A). The difference in the sizes of the agNps suggests that they were capped by proteins and polyphenolics compounds of different molecular weights to confer stability. Stability was further determined by Zeta potential measurements.

Zeta potential is the important measurement to determine the stability of TIAgNps. It reveals the electrostatic repulsion forces present among similarly charged nanoparticles in a colloidal medium. In this study the zeta potential value of the synthesized leaf AgNps was calculated as - 32.6mV(Fig 3B). This high negative value confers good colloidal nature, long-term stability and high dispersity of AgNps without any aggregation. The long term stability is very essential for the biomedical applications of AgNps.




Figure 3: DLS Chromatogram Of Silver Nanoparticle Of T.indicum Leaf Extract, Particle Size(A) And Zeta Potential Measurement(B)

After isolation, preparation, analysis and characterization of AgNps the following aspects were performed to confirm its inhibitory activity on Russell viper venom using blood as sample.

Hemolytic Inhibition

Hemolytic activity is a distinct feature of snake venoms that is greatly induced by multicomplex molecules like metalloproteases, PLA₂ and more specifically, cardiotoxins and cytotoxins of venom (Osorio *et al* 1989 and Fletcher *et al* 1991). The RBC from direct hemolytic activity of snake venom as cardiotoxins and cytotoxins can induce lysis of human erythrocytes however it is possible that the phytochemicals of plants could inhibit these toxins of the venom.

Enzymatic and inhibition studies using TIAgNps has revealed that the *T.indicum* was able to inhibit, phospholipase $A_2(PLA2)$ and hemolytic enzymes present in the Russell viper venoms at 10 μ g/mL

concentrations with a promising inhibiting effect of Russell viper toxins. The leaf and stem nano particles have inhibited venom PLA2 activity by 90.25% and 89.89% respectively.

Blood Diffusion:

The hemolysis of blood was tested for Russell viper venom using zones of lysed blood on blood mixed in agar plates. The results of Figure 4 have shown that the Russell viper had hemolysis and the concentration was taken from the haemolytic inhibition assay. The three different concentrations ie, 10, 20 and 30μ gs were tested. The protection for Russell viper for leaf extract was at 10μ g where as for stem extract at 20μ g. The zone of diameter was measured for three concentrations in millimeters. Among all the concentrations of leaf and stem showed inhibition of neutralization of venom on blood agar plates (Figure 4A, B, C and Table.3).




Fig 4:Russell viper Venom Diffusion studies in agar plates (A 10µg, B 20µg and C 30µg)

Tab	ole:	2	Antiv	enomic	Effect	Analysis	Of	T.indicum	AgNps	On
Blo	od A	١g	ar Pla	tes By N	leasuri	ng The Zo	ne (Of Inhibitio	on (in M	m)

Sample	Concentrations (µg/ml)			
	10	20	30	
Control	0.7	0.7	0.7	
Control+Stem	0.9	1.0	1.4	
Control+Leaf	0.6	1.2	1.3	
Russell viper +stem	1.1	1.1	1.4	
Russell viper + Leaf	0.8	0.9	0.9	

The blood discs which had been impregnated with a series of leaf and stem AgNps were placed on agar surface in a Petri plates. The agar plate was then incubated at 37°C for 18 to 24 hours. After the incubation, the plates were examined for inhibition zone. The inhibition zone was then measured. The test was repeated thrice to ensure reliability. Then the blood agar plates were taken for fluorescent microscopy and observed the changes that were occurred in control (Fig 5A), Russell viper toxins (Fig 5B) and *T indicum* AgNps (Fig 5C & D). From Figure 6 it was observed that in the absence of dye to the erythrocytes and the changes observed under the fluorescence were normal intact erythrocytes (Control, Fig 6A), erythrocyte blubbing on venom treatment (Fig 6B), erythrocyte protection in leaf AgNps (Fig 6C) and stem AgNps (Fig 6D). These two microscopic studies reveal that the results of hemolysis were similar in change of morphology of erythrocytes.




Fig:5 Fluorescent Microscopic Analysis Blood Cells Stained With Giemsa Dye And Mixed With Effectors Of Venom.

Note: A) Control: Cells are intact and not lysed as that of venom, B) Russell viper's venom: The arrows point outs the Clump of cells as smear, C) Russell viper's venom plus leaf AgNps: Some of the cells are ruptured, and D). Russells viper venom plus stem AgNps: The arrow indicated represents Cells intactness




Fig:6 Microscopy Of Blood Agar In Absence Of Dye And Fluorescence

Note: A) Control blood Cells were normal and intact in freshly prepared slide, B) Russell viper venom plus blood : Cells size is normal but blebbing is seen, \hat{C}) Russell viper venom plus leaf AgNps : Cells are normal and protection against venom was found and D) Russell viper venom plus stem AgNps.

CONCLUSION:

Much attention was drawn for the benefits of plant-based formulations and their bioactive molecules/compounds for the treatment of infections, inflammations and other diseases. Earlier researchers studied on the neutralization parameters of snake venom using blood by plant molecules have compromised our results with respect to their anti-venom action on the medicinal plant extracts. Our results and procedures applied shall show that the efficacy of a plant AgNps against the intoxication of venom. The present study shows that the Trichodesma indica with its sliver nanoparticles could inhibit snake venom activity by the inhibiting of phospholipases and venom other proteiases. In conclusion, the observations confirmed that the nanoparticle extracts of T.indicum possesses potent snake venom neutralizing properties. Thus it may be used as an alternative treatment to serum therapy and as a rich source of potential inhibitors of toxins.

Acknowledgments:

The authors acknowledge the financial supportprovided by UGC New Delhi and some work made by PG students.

REFERENCES:

- Alam MI, Gomes A: Snake venom neutralization by Indian medicinal plants (*Vitex negundo and Emblica officinalis*) root extracts. J Ethnopharmacol 2003, 86(1):75-80.
- Alarmal Mangai S. and Subban Ravi Comparative Corrosion Inhibition Effect of Imidazole Compounds and of *Trichodesma indicum* (Linn) R. Br. on C38 Steel in 1M 2.
- HCl Medium Journal of Chemistry. 2013, 1-4 (Article ID 527286) Ali SS, Kasoju N, Luthra A, Singh A, Sharanabasava H, Sahu A, Bora U Indian medicinal herbs as sources of antioxidants. Food Res Int 2008, 41:1-15 3
- Anusha SU, Sundar SK, Murugan Manavalan, Isolation and Screening of Bacterial Isolates in UTI Patients in Different age and Gender Groups in Namakkal District, Tamil 4
- Nadu Journal of Applied Pharmaceutical Science 2014, 4 (09) 0027-029. Artz RR., Chapman S., Siegenthaler A., Mitchell EA., Buttler A., Borotoluzzi E Functional microbial diversity in regenerating cutover peat lands responds to vegetation 5. succession 2008, 45(6) 1799-1809
- Ashok B., Bhagyashree J., Ameeta RK., Smita Z. Banana peel extract mediated novel 6. route for the synthesis of silver nanoparticles. Colloids Surf A Physicochem Eng Aspects. 2010,368:58-63
- 7. Bhavya Janardhan, Vineetha M Shrikanth, Kiran K Mirajkar and Sunil S. More In vitro screening and evaluation of antivenomphytochemicals from Azima tetracantha Lam leaves against Bungarus caeruleus and Vipera russelli, Journal of Venomous Animals and Toxins including Tropical Diseases 2014, 20:12 Boman HG, Kaletta U. Chromatography of rattlesnake venom; a separation of three
- 8. phosphodiesterases. Biochim Biophys Acta. 1957, 24(3):619-631 Fissan H., Ristig S., Kaminski H., Asbach C., Epple M. Comparison of different
- 9. characterization methods for nanoparticle dispersions before and after aerosolization. Anal. Methods 2014, 6: 7324-7334.
- FletcherMS., Jiang OH., Gong ML., Yudkowsky SJ., Wieland. Effects of a cardiotoxin from Naja naja kaouthia venom on skeletal muscle: involvement of calcium-induced 10 calcium release, sodium ion currents and phospholipases A2 and C, Toxicon 1991. (29)1489-1500.
- Gopi K., Anbarasu Kadali Renu., Jayanthi S., Vishwanath BS., Gurunathan Jayaraman. 11. Quercetin-3-O-rhamnoside from Euphorbia hirta protects against snake Venom induced toxicity Biochimica et Biophysica Acta 2016, 1860(7) 1528-154
- Gurunathan S, Park JH, Han JW, Kim JH Comparative assessment of the apoptotic potential of silver nanoparticles synthesized by Bacillus tequilensis and Calocybe indica

- in MDA-MB-231 human breast cancer cells: targeting p53 for anticancer therapy. 2015, 29.10(1) 4203-4223 Gutiérrez J M., Avila C., Rojas E. & Cerdas L.An alternative in vitro method for testing 13. the potency of the polyvalent antivenom produced in Costa Rica. Toxicon. 1988;
- 26(4):411-3 Gutierrez JM., Williams D., Fan HW., Warrell DA., Snake bite envenoming from a 14.
- lobal perspective: towards an integrated approach, Toxicon 2010, 56 1223-1235 Habermann E, Neumann W. Characterization of the effective components of snake venoms Naunyn Schmiedebergs Arch Exp Pathol Pharmakol. 1954, 223(5):388-98. 15
- Kadali VN, Kindangi KR. Ethno-medicinal plants used by the Traditional healer of West Godavari District, Andhra Pradesh, India. Journal of pharamacognosy and 16. Phytochemistry. 2015; 3(6):117-118.
- Khan T, Ahmad M, Khan R, Khan H and Choudhary MI phytotoxic and insectidial activites of medicinal plants of Pakistan Trichodesma indicum, Aconitum laeve and 17. Sauromatum guttatum Journal of the Chemical Society of Pakisthan 2008, 30: (2) 251-
- Kora AJ., Sashidhar RB., Arunachalam J. Aqueous extract of gum olibanum (Boswellia serrata): a reductant and stabilizer for the biosynthesis of antibacterial silver 18. nanoparticles. Process Biochem.2012,47: 1516-1520.
- Lang CE, Macdonald JR, Reisman DS, Boyd L, Jacobson Kimberley T, Schindler-Ivens SM, Hornby TG, Ross SA, Scheets PL. Observation of amounts of movement practice 19.
- provided during stroke rehabilitation. Arch Phys Med Rehabil. 2009,90(10):1692-8. Li WR., Xie XB., Shi QS., Zeng HY., Ou-Yang YS., Chen YB. Antibacterial activity and 20. mechanism of silver nanoparticles on Escherichia coli. Appl. Microbiol. Biotechnol. 2010.8:1115-1122.
- 21. Litvin VA., Minaev BF. Spectroscopy study of silver nanoparticles fabrication using synthetic humic substances and their antimicrobial activity. Spectrochim Acta Part A 2013.108:115-122
- Mohapatra B., Warrell DA, Suraweera W, Bhatia P, Dhingra N., Jotkar RM, Rodriquez PS., Mishra K., Whitaker R., Jha P. Million death study collaborators, 22 snakebite mortality in India: a nationally representative mortality survey, PLoS Negl. Trop. Dis. 2011: (5)e1018.
- Hop, Dis. 2011, Options. Mukherjee P., Ahmad A., Mandal D., Senapati S., Sainkar SR., Khan MI.,Renu P., Ajaykumar PV., Alam M., Kumar R. Fungus-mediated synthesis of silver nanoparticles and their immobilization in the mycelial matrix: A novel biological approach to nanoparticle synthesis. Nano Lett. 2001, 1:515-519. Murdock RC., Braydich-Stolle L., Schrand AM., Schlager JJ., Hussain SM.
- 24. Characterization of nanomaterial dispersion in solution prior to in vitro exposure using dynamic light scattering technique. Toxicol. Sci. 2008, 101: 239-253. Oliveira HC., WulffA., Saviani EE, Salgado I Nitric oxide degradation by potato tuber
- 25 mitochondria: evidence for the involvement of external NAD(P)H dehydrogenases. Biochm Biophysics Acta 2008, 1777:470-476.
- Osorio e Castro, L.P. Vernon, Hemolytic activity of thionin from Pyrularia pubera nuts and snake venom toxins of Naja naja species: Pyrularia thionin and snake venom 26
- and shake venom toxins of vaga faga species. Fyrtuant monin and shake venom cardiotoxin compete for the same membrane site, Toxicon. 1989, 2.7 511-517 Perianayagam JB., Narayan S., Gnanasekar G., Pandurangan A., Raja S., Rajagopal K., Rajesh R., Vijayarakumar P. and Vijaykumar SG. Evaluation of antidiarrheal potential of *Emblica officinalis*. Pharmaceutical Biology.2005, 43(4): 373-377 Perianayagam JB., Sharma SK., Pillai KK. Anti-inflammatory activity of *Trichodesma* 27.
- 28. indicum root extract in experimental animals. J. Ethnopharmacol. 2006, 104: 410-414 Periyanayagam JB., Sharma SK., Pillai KK., Pandurangan A., Kesavan D. Evaluation of
- 29 artimicrobial activity of ethanol extract and compounds isolated from *Trichodesma* indicium (Linn.) R.B.rroot. J Ethnopharmacol. 2012, 142(1): 283-286 Pleus R. Nanotechnologies - Guidance on Physicochemical Characterization of Engineered Nanoscale Materials for Toxicologic Assessment; ISO: Geneva,
- Switzerland, 2012.
- Ram Krishna and Chattrerjee. Preliminary phytochemical, Antioxidant and antimicrobial activities of different extracts of Cassia tora and Trichodesma indicum Int'l 31.
- Jof Pharm & Tech. 2016, 8 (2): 12578-12597
 Santhosh MS, Hemshekhar M., Sunitha K., Thushara RM., Jnaneshwari S, Kemparaju K., Girish K.S. Snake venom induced local toxicities: plant secondary metabolites as an auxiliary therapy. Mini Rev. Med. Chem. 2013, 13: 106-123.
 Sanghi R., and Verma P. Biomimetic synthesis and characterization of protein capped bibling in the Direct Technology. 109: 601-109. 32.
- silver nanoparticles. Biores Technol. 2009, 100:501-504 Schwinté P., Foerstendorf H., Gärtner W., Mroginski M.A., Hildebrandt P., and Siebert F.
- 34. Fourier transform infrared studies of the photoinduced processes of phytochrome A using isotopically labelled chromophores and density functional theory calculations.
- 35.
- using isotopically labelled chromophores and density functional theory calculations. *Biophys. J.* 2008, (95)1256-1267.
 Shaw, George&Nodder, Fredrick P (Eds) 1797, The Naturalist Miscellany, Vol VIII, London, Nodder & Co., plates 255-300, 180 unnumbered pps.
 SriKanth K., Murugesan T., Anil Kumar Ch., Suba V Das., AK Sinha S. Effect of *Trichodesma indicum* extract on cough reflex induced by sulphur dioxide in mice Phiomedicine. 2002, 9(1)75-77 36
- Suman B., Eswarai B., Divya BJ., Pallavi C., swamy MV., Kemparaj K and Thyagaraju 37 Suman D, Loward D, Drya DS, and Ye, Swany WV, Kenpang K and Hyggardy K Effect of Silver nanoparticles synthesized of *Trichdesma indicum* against Naja naja (cobra) venom, JJPSR 2018, 9(8) 3291-96. Doi:10.13040/ijpsr 0975-8232 9(8)3291-96. Thirunavoukkarasu M., Balaji U., Behera S., Panda PK., Mishra BK. Biosynthesis of
- 38. Silver nanoparticle from leaf extract of Desmodium gangeticum (L.) DC. and its biomedical potential. Spectrochim Acta Part A. 2013, 116:424-427 Vanaja K., Paulkumar G., Gnanajobitha S., Rajeshkumar C., Malarkodi and . Annadurai G. Herbal Plant Synthesis of Antibacterial Silver Nanoparticles by Solanum
- 39 trilobatum and Its Characterization International Journal of Metals Volume 2014, Article ID 692461,1-8pp Vanitha K, Baskaran K, Periyasamy D, Saravanan A, Ilakkia S, Selvaraj R,
- Venkateswari A. Review on the Biomedical Importance of Taurine Journal of Pharma Research and Health Sciences. 2015, 3 (3)680-686. International
- Verma N., Tripathi SK., Sahu D., Das HR. Evaluation of inhibitory activities of plant extracts on production of LPS-stimulated pro-inflammatory mediators in J774 murine macrophages. Mol. Cell. Biochem. 2010, 336:127-135.

83