



## THE EFFECT OF BIOCERAMIC SEALERS WITH BIOCERAMIC IMPREGNATED GUTTA PERCHA ON THE FRACTURE RESISTANCE OF ENDODONTICALLY TREATED TEETH – AN IN VITRO STUDY

<b>Dr Naveen Kumar K</b>	MDS, Reader, Department of Conservative Dentistry and Endodontics, KVG Dental college and hospital Sullia, Dakshina Kannada, Karnataka, India 574327
<b>Dr Krishna Prasada L</b>	MDS, HOD, Department of Conservative Dentistry and Endodontics, KVG Dental college and hospital Sullia, Dakshina Kannada, Karnataka, India 574327
<b>Dr Nihala Mariyam*</b>	Post graduate student, Department of Conservative Dentistry and Endodontics, KVG Dental College and hospital Sullia, Dakshina Kannada, Karnataka, India 574327*Corresponding Author
<b>Dr Ramya M.K</b>	Reader, Department of Conservative Dentistry and Endodontics, KVG Dental college and hospital Sullia, Dakshina Kannada, Karnataka, India 574327

**ABSTRACT** **Aim:** To compare and evaluate the effect of Bioceramic sealers with Bioceramic Impregnated Gutta Percha on the fracture resistance of endodontically treated teeth. **Materials and methods:** A total of thirty single-rooted mandibular premolar teeth were decoronated to standardize the root length of 13mm. Cleaning and shaping was done and the samples were randomly divided into three groups. Group I: Bioceramic Sealer (Ceraseal B) with Bioceramic Impregnated Gutta Percha (SURE ENDO), Group II: Bioceramic Sealer (Ceraseal B) with normal Gutta Percha, Group III: AH Plus sealer along with normal gutta-percha. All the teeth were embedded in acrylic resin blocks and fracture force was measured using a universal testing. Then, the data will be statistically evaluated using two-way analysis of variance (ANOVA). **Results:** The fracture resistance of group III > group II > group I. However, the results were statistically not significant. Ceraseal-B sealer along with bioceramic impregnated gutta-percha (BIO-GP) showed the maximum fracture resistance compared to the other two groups. **Conclusion:** From this study, it can be concluded that the fracture resistance of Ceraseal-B sealer with Bio GP Points was better than that of Ceraseal-B sealer with traditional gutta-percha, although the difference was not statistically significant. The bioceramic sealer (Ceraseal-B) combined with Bio GP Points had a better fracture resistance than that of AH Plus sealer with traditional gutta-percha and the difference was statistically significant.

**KEYWORDS :** Bioceramic Sealer (Ceraseal B); Bioceramic impregnated Gutta Percha

### Introduction:

Vertical root fracture (VRF) is one of the most common complication of the endodontically treated tooth.<sup>1</sup> This is due to over instrumentation of the canal, dehydration of dentin after endodontic therapy, uncontrolled pressure during obturation.<sup>2,4</sup> Obturation materials are play vital role in supporting strength of the endodontically treated teeth.<sup>5</sup> The most commonly used root canal filling material is gutta-percha in combination with sealer, but the low elastic modulus of gutta-percha presents little or no capacity to reinforce roots after treatment.<sup>6</sup> Gutta percha has poor sealing ability and its inability to further strengthen the teeth, increases its susceptibility to fracture.

New bioceramic impregnated gutta percha (BIO-GP) was introduced into the market. The manufacturers claim that it can create monoblock obturation in root canal when used with bioceramic sealer and form a true gap-free seal.<sup>7</sup>

Ceraseal-B is a newly introduced MTA based bioceramic sealer which resin and monomer free and ensures zero shrinkage and biocompatibility. Its high pH and bioactive properties help remineralization due to hydroxy-apatite formation. It is thought that adhesion and mechanical interlocking between the root canal filling material and radicular dentin reduces the risk of fracture and strengthens the remaining tooth structure.<sup>8</sup>

### Methodology:

A total of thirty single-rooted mandibular premolar teeth will be collected. The teeth with calcified canals, cracks or fractures, development defects, multiple canals, root caries, and endodontically treated teeth were excluded. The teeth were decoronated to standardize the root length of 13mm. Cleaning and shaping will be done with Protaper Gold files. The canals was irrigated by using 5 mL 3% NaOCl solution, and as soon as the instrumentation is completed, the smear layer was removed by flushing the root canals with 5 mL 17% ethylenediaminetetraacetic acid solution then irrigated again with NaOCl. Finally, the canal was flushed with 3 ml distilled water then dried with paper points. The teeth were then divided into three groups.

- Group I: Bioceramic Sealer (Ceraseal B; MAARC) with Bioceramic Impregnated Gutta Percha (BIO-GP; SURE ENDO)
- Group II: Bioceramic Sealer (Ceraseal B; MAARC) with traditional Gutta Percha
- Group III: AH Plus sealer along with traditional gutta-percha.


To permit the sealers to fully set, the specimens was kept in incubator for 7 days (at 37°C and 100% relative humidity). To simulate a periodontal ligament, the root surface was covered with a thin-layer polyvinylsiloxane impression material to 2 mm apical to the coronal end of the root. Each tooth was then mounted vertically into acrylic resin exposing only 2 mm from the root using a plastic ring as a mould for packing acrylic. Fracture resistance testing was done using a universal testing machine. A cylindrical steel rod with round tip 2 mm in diameter attached to the upper part of the universal testing machine was used to apply force on the root at a crosshead speed of 1 mm/min until fracture occurred. The maximum force required to fracture each specimen was recorded in Newtons (N).

### Statistical analysis:

All statistical analysis was performed by using the SPSS software. The mean and the standard deviation were calculated for each variable. Analysis of the data between groups was carried out by 2- way analysis of variance (ANOVA).  $P < 0.05$  was considered as statistically significant.

### Results:

The mean fracture resistance (MPa) and standard deviations (SD) of all the three groups are given in table 1. The highest mean of fracture resistance was found in Group I (BIO-GP + Ceraseal-B) 421.340 N, followed by Group II (GP + CEARSEAL-B) 465.8 N, while Group III (GP + AH-Plus) shows the least mean 399.9N (table no. 1). 2-way ANOVA test exhibited significant differences ( $p=0.0303$ ) among the groups. Post hoc analysis showed significant differences ( $p=0.0237$ ) between group III and group I specimens (Graph 2) whereas the mean difference seen between group 1 and group 2 as well as between group 2 and group 3 was not statistically significant.




**Graph 1: Mean value of fracture resistance of all groups**

**Table no. 1 – Mean, standard deviation, and test of significance using ANOVA between the three groups.**

Group Name	Number of samples	Mean and standard deviation	Minimum	Maximum	P- value
Group 1	10	470.51±66.01	380.6	560.8	0.000006*
Group 2	10	388.38±64.48	284.8	465.8	
Group 3	10	287.92±36.29	235.7	345.7	

\*P value < 0.05 is considered as statistically significant.



**Graph 2 : difference in mean levels of groups**

Results inference - There is a statistically significant difference that exists between all the 3 groups.

**Discussion:**

Obturation material has a potential to strengthen the root structure and increases fracture resistance of tooth.<sup>9</sup> In the present study, Ceraseal-B sealer along with bioceramic impregnated gutta-percha (BIO-GP) showed the maximum fracture resistance compared to the other two groups. The reason for this was good bonding between bioceramic particles. This bonding forms a primary monoblock pattern which improves the strength of the sealer with dentin and thus reducing the stress that occurs inside the tooth structure.<sup>10</sup> Also, the Bioceramic coated gutta percha cones has the capability to absorb water from the tooth environment and expand in the lateral direction only to hermetically seal the root canal.<sup>11</sup> This study is in consistent with the results of Celikten et al who reported root canal obturation with bioceramic sealer and bioceramic gutta percha strengthened the prepared root.<sup>12</sup> The result of this study was also in accordance with the study conducted by Hasnain, et al. and Sağsen et al.<sup>13,14</sup> In a study performed by Gerverni et al showed that the roots filled with either Bc Sealer/ Bioceramic – Coated Points or AH Plus Sealer/conventional gutta percha points gutta showed similar resistance to fracture. In an another study by Osiri et al showed that the fracture resistance of BCC/BCS was higher than GP/AH.<sup>16</sup> In this study, BCS showed better fracture resistance than AH Plus sealer. This may be due to the formation of chemical bond with dentine through hydroxyapatite production during setting in bioceramic sealers.<sup>11</sup> Also due to BC Sealer's ability to penetrate dentinal tubules and interact with dentine moisture, optimum dimensional stability and the least amount of shrinkage was obtained.<sup>17</sup> Han and Okiji et al stated that permeation of the sealer's mineral content into the intertubular dentine results in denaturing the collagen fibers and the formation of a mineral infiltration zone.<sup>18</sup> This can be explained by the incorporation of Ca and Si in dentin with subsequent chemical, physical and structural modification of dentin, resulting in higher fracture resistance and strength.<sup>19</sup> This results was in accordance with other studies such as

Patil et al., Nagpal et al and Cobankara et al.20-22 Delong et al. in his study concluded that Bioceramic sealer showed highest strength than AH plus sealer when used in a single cone technique.<sup>15</sup> In contrast with Dibaji et al., which found that bioceramic group showed less fracture resistance than AH Plus.<sup>23</sup>

**CONCLUSION:**

From this study, it can be concluded that the fracture resistance of Ceraseal–B sealer with Bio GP Points was better than that of Ceraseal – B sealer with traditional gutta-percha, although the difference was not statistically significant. The bioceramic sealer (Ceraseal- B) combined with Bio GP Points had a better fracture resistance than that of AH Plus sealer with traditional gutta-percha and the difference was statistically significant. However, further in-vitro and in-vivo studies with a larger sample and the teeth with complex anatomies are required to validate its clinical efficacy.

**REFERENCES:**

- Reinhardt RA, Krejci RF, Pao YC, et al. Dentin stresses in post reconstructed teeth with diminishing bone support. J Dent Res 1983;62(9):1002–1008.
- Sedgley CM, Messer HH. Are endodontically treated teeth more brittle? J Endod 1992;18(7):332–335. DOI: 10.1016/S0099-2399(06)80483-8.
- Reinhardt RA, Krejci RF, Pao YC, et al. Dentin stresses in post reconstructed teeth with diminishing bone support. J Dent Res 1983;62(9):1002–1008..
- Trope M, Ray Jr HL. Resistance to fracture of endodontically treated roots. Oral Surg Oral Med Oral Pathol 1992;73(1):99–102.
- Gulsahi K, Cehreli Z, Kuraner T, et al. Sealer area associated with cold lateral condensation of Gutta-percha and warm coated carrier filling systems in canals prepared with various rotary NiTi systems. Int Endod J 2007;40(4):275–281. DOI: 10.1111/j.1365-2591.2006.01213.x
- F. C. Ribeiro, A. E. Souza-Gabriel, M. A. Marchesan, E. Alfredo, Y. T. C. Silva-Sousa, and M. D. Sousa-Neto, "Influence of different endodontic filling materials on root fracture susceptibility," Journal of Dentistry, vol. 36, no. 1, pp. 69–73, 2008.
- Evaluation of Push out Bond Strength of Different Endodontic Sealers with Different Obturation Techniques Yousra Aly and Sherif El Shershaby Restorative and Dental Materials Department, National Research Centre, 33 El-Buhouth St., 12622 Dokki, Giza, Egypt. Received: 20 June 2020 /
- Scha'fer E, Zandbiglari T, Scha'fer J. Influence of resin-based adhesive root canal fillings on the resistance to fracture of endodontically treated roots: an in-vitro preliminary study. Oral Surg Oral Med Oral Pathol Oral Radiol Endod 2007;103:274e9.
- N. A. Shaheen, A. M. Farag, H. A. Alhadainy, and A. M. Darrag, "Fracture resistance of endodontically treated roots using different preparation-obturation combinations," Tanta Dental Journal, vol. 10, no. 2, pp. 97–102, 2013.
- Sharma S. The viability of current obturating systems as Replacement Endodontic Monoblocks – A 3- Dimensional Finite Element Analysis. Endodontology. 2014 Dec;26(2).
- Sly MM, Moore BK, Platt JA, Brown CE. Push-out bond strength of a new endodontic obturation system (Resilon/Epiphany). J Endod. 2007;33(2):160-2.
- Celikten B, Uzuntas CF, Gulsahi K. Resistance to fracture of dental roots obturated with different materials. Biomed Res Int 2015;2015:1–5.
- Hasnain M, Bansal P, Nikhil V. An in vitro comparative analysis of sealing ability of bioceramic-based, methacrylate-based, and epoxy resin-based sealers. Endodontology. 2017 Jul 1;29(2):146.
- Sağsen B, Üstün Y, Pala K, Demirbuğa S. Resistance to fracture of roots filled with different sealers. Dental materials journal. 2012 Jul 30;31(4):528-32.
- Akçay M, Arslan H, Durmus N, et al. Dentinal tubule penetration of AH plus, iRoot SP, MTA Fillapex, and GuttaFlow Bioseal root canal sealers after different final irrigation procedures: a confocal microscopic study. Lasers Surg Med 2016;48(1):70–76.
- Osiri S, Banomyong D, Sattabanasuk V, Yanpiset K. Root reinforcement after obturation with calcium silicate-based sealer and modified gutta-percha cone. Journal of endodontics. 2018 Dec 1;44(12):1843-8.
- Bayram H, Brayam E, Kanber M, Celikten B, Saklar F. Effect of different chelating solutions on the pushout bond strength of various root canal sealers. Biomed Res 2017; (Special issue): S401-6.
- Raghavendra SS, Jadhav GR, Gathani KM, Kotadia P. Bioceramics in endodontics—a review. Journal of Istanbul University Faculty of Dentistry. 2017;51(3 Suppl 1):S128.
- Melo MA, Cheng L, Zhang K, Weir MD, Rodrigues LK, Xu HH. Novel dental adhesives containing nanoparticles of silver and amorphous calcium phosphate. Dental Materials. 2013 Feb 1;29(2):199-210.
- Patil P, Banga KS, Pawar AM, et al. Influence of root canal obturation using gutta-percha with three different sealers on root reinforcement of endodontically treated teeth. An in vitro comparative study of mandibular incisors. J Conserv Dent 2017;20(4):241–244.
- Nagpal A, Annapoorna BM, Prashanth MB, et al. A Comparative Evaluation of the Vertical Root Fracture Resistance of Endodontically Treated Teeth The Journal of Contemporary Dental Practice. 13(3):351–355. doi:10.5005/jp-journals-10024-1150
- Cobankara FK, Ungor M, Belli S. The effect of two different root canal sealers and smear layer on resistance to root fracture. J Endod 2002;28(8):606–609. DOI: 10.1097/00004770-200208000-00011.
- Dibaji F, Afkhami F, Bidkhor B, et al. Fracture resistance of roots after application of different sealers. Iran Endod J 2017;12(1):50–54.