

## Use of Geosynthetic Material Under Fatigue and Rut Tests



### Engineering

KEYWORDS : Rut Test, Fatiuge Beam test etc

Dhaval. V. Sheth

M.E Civil Engineer, Transportation Engineering, L.D.ENgg. College, Gujrat, India

### ABSTRACT

*Geosynthetics, used for drainage, separation and reinforcement, are in two forms,- Woven - cloth-like materials with fibers woven perpendicular to each other.- Non-woven - felt-like materials with randomly-oriented fibers. Geosynthetic for pavement rehabilitation provide the functions such as waterproofing, stress absorption and reinforcement between the old and new asphalt concrete overlay. There are a number of different Geosynthetic materials, and with the similarity of many of the names, as well as much similar sounding trade names. The greatest future benefit of Geosynthetic materials is likely to be realized in pavement structures as well as a clearer valuation of immediate and life-cycle cost and benefits. A Geosynthetic material when used with asphalt concrete has shown a serviceable life equivalent to that of an overlay. In this Paper Presentation deals the fatigue test and rut test using with Geosynthetic material. During My Research 3 Types of Geosynthetic Materials used for Wheel Tracking test & Fatiuge Beam test carried out. After all test result, I found that Geosynthetic material have more Tensile Strength, Economical and improve pavement life as compare to PMB material used.*

### 1. INTRODUCTION

Maintenance of pavements involves two stages viz. routine maintenance and periodic maintenance. If the routine maintenance is delayed, there are chances of development of cracks. Movements concentrated around pre-existing cracks are unable to withstand shear and tensile stresses which create the crack. This movement may be due to the traffic loading which causes differential deflections at cracks in the underlying pavement layers, expansion or contraction of subgrade soils and, of the pavement itself due to changes in temperature, or combination of these phenomena. When these stresses become greater than the shear or tensile strength of the HMA, cracks develop in the new overlay. This propagation of an existing cracking pattern from the old pavement into and through a new overlay is known as reflective cracking. The full range of Geogrids has been specially developed for asphalt reinforcement. It adds to the strength of road, it is designed to turn crack stresses horizontally and dissipate the stress. As reinforcement, it increases the tensile strength characteristics of asphalt concrete. Geogrid for pavement rehabilitation provide the functions such as waterproofing, stress absorption and reinforcement between the old and new asphalt concrete overlay. This report deals with the use of different Geogrid material and comparing their strength parameters viz, rutting, fatigue life

#### 1.1 Scope of work

In my work I have tested various types of Geogrid material and carried out fatigue and rut test using with different types of Geogrid material. In fatigue test a beams were prepared using with different types of material, tested and Geogrid finding a fatigue life. In rut test slabs were prepared and tested on rut testing machine for a 20, 000 cycles or 20 mm rut depth which is earlier.

#### 1.2 Methodology

The overall methodology involves following steps;

1. The Initial step of methodology was Literature review which contains propagation and mechanism of reflective cracking and measures to retard it including information regarding Geogrid material.
2. The second step was studying the physical properties of aggregates, bitumen and Geogrid material. Further test like indirect tensile strength, fatigue test and rutting test were carried out.
3. The third step was Marshall Mix design. Later Geogrid material was tested and fatigue and rut tests were conducted.
4. The fourth step was evaluation of cost-economics include consideration.

The last step was conclusion that, which Geogrid material was best for road construction

## 2. LITERATURE REVIEW

### 2.1 Defects in bituminous surfacing

The defects in bituminous surfacing may be grouped into four categories as per C.Venkettappa (Transportation Engg.)

- (i) Surface defects which include fatty surface, smooth surface, streaking & hungry/dry surface.
- (ii) Cracks viz. Block cracking, Fatigue cracks, alligator cracks, longitudinal cracks, edge cracks, shrinkage cracks and Reflective cracks.
- (iii) Deformation defects which include slippage, rutting, corrugation, shoving, shallow depressions and settlements.
- (iv) Disintegration defects which includes stripping, loss of aggregates, raveling, pot-holes and edge breaking.

### 2.2 Mechanism Of Fatigue Crack Propagation

Fatigue is the general phenomenon of material failure due to the growth of microscopic flaws as a result of repeated loading. These micro-cracks become more visible as the stress concentrations at the tip of the crack increases and causes further crack propagation. Paris' Law, as provided in equation

$$Dc/dN = A (\Delta K)^n \text{----- (2.1)}$$

Where

C = crack length

N = number of load application

Dc / dN = rate of crack growth {or "crack speed"}

$\Delta K$  = change of stress intensity factor during loading

A, n = fracture parameters for the asphalt mixture

In 1921, Griffith provided a criterion, which stated, "Crack propagation would occur if the energy released upon crack growth is sufficient to provide all of the energy that is required for crack growth".

### 2.3 Measures to Control Reflective -Cracking

Over the past several decades, extensive research work was carried out to reduce the problem of reflection cracking. Some of the measures attempted are discussed here briefly.

#### 2.3.1 Use of Polymer Modified Bitumen

EVA (Ethyl Vinyl Acetate) and SBS (Styrene Butadiene Styrene) polymer modified bitumen were successfully used as overlay binders in the construction of bituminous overlays placed over concrete carriageways said by S.K. Patil. ADOT placed their first stress absorbing membrane interlayer (SAMI), an interlayer designed to reduce reflective cracking in an overlay. Both the SAM and SAMI were designed to utilize the enhanced elastic properties of the rubber - modified binder in the rehabilitation of a cracked pavement and their applications showed great promise in reducing reflective cracking


#### 2.3.2. Use of Geogrid.

Use of geosynthetic for interlayer underneath the asphalt overlay has been found to improve the reflection cracking properties of the overlays according to S.K. Patil, (Reflective Cracking of Bituminous Overlays- A Laboratory Investigation, INDIAN HIGHWAYS Vol. 31 No 5 P 5- 14). Geosynthetics is a non-woven polypropylene membrane approximately 1 mm thick and is usually laid on a binder film of about 1 mm thick. Geotextile act as reinforcement interlayer and are expected to

- (a) Absorb the tensile stresses, which develop in the bituminous overlay.
- (b) Provide strain release.
- (c) Block the penetration of water from the surface of the cracked pavement to the lower layers.

**2.4 The Main Geogrid Characteristics**


The Main Geogrid Characteristics as per Geosynthetic, British Columbia (Ministry of agriculture and lands),



(Figure 2.1 : Main Geogrid characteristics.)

**2.5 Hot mix overlay**

Standard paving operations should closely follow fabric layout. All areas in which paving fabric has been placed should be paved during the same day. If the fabric becomes wet, it must be allowed to dry completely before paving. A minimum compacted asphalt thickness of 1” to 1.5” Is required depending on roadway volume.



**1. Cleaning 2. Filling of 3.Applying 4.Spraying 5.Laying of Cracks Tack-coat Geogrid Bitumen (Photograph 2.1: installation guidelines)**

**3. LABORATORY TEST**

**3.1 Physical Properties of the Aggregates**

The aggregates in the obtained Mix were tested for various physical properties such as stripping value, water absorption, impact value, flakiness and elongation indices and the results were obtained from the site and the sample was collected and tested as per IS-2386 & IS:6241 Codes.

**3.2 Physical Properties Of Bitumen**

The bitumen used for the mix was also tested for the required properties i.e. Penetration Test (IS 1203-1978), Softening Point (IS 1205-1978), Specific Gravity and Ductility (IS 1208-1978) by IS Codes.

**3.3 Testing of Geogrid**

Geogrid is to be tested for many properties before using in roads as an inter/ intra layer. Placing of Geogrid material like TGU-40, TGU-80, TGU100, which acts as a stress absorbing membrane? Following test were carried out on Geogrid are explained in the following sequence:-

**3.3.1 Asphalt retention.**

As per ASTM: D 6140-97, Standard Method to Determine Asphalt Retention of Paving Fabrics Used in Asphalt Paving for Full-Width Applications

**3.3.2 Melting point.**

This test was conducted as per AASHTO M 288-92, Standard Specifications for Geogrid Specification for Highway Application. The Geogrid was placed in the oven at 165 deg. for 24 hrs.

**3.3.3 Tensile Strength.**

Tensile strength is the most important parameter, as it will define

the Geogrid able to act as a stress absorbing membrane. The tensile strength is measured on tensile strength measuring instrument. A sample of Geogrid is adjusted in the jaws of the machine such that the length between the two jaws is about 20 cm. The reading is taken until the reading decreases in the dial gauge.

**3.3.4 Stripping Of Geogrid**

This test was conducted as per G. Dondi, Laboratory Test on Bituminous Mixes Reinforced by Geogrids, Rilem-199 the stripping of the asphalt coated Geogrid sample was determined to know the susceptibility of Geogrid towards water. The Geogrid coated with bitumen as per the asphalt retention procedure, then the Geogrid was placed in water at 40 deg for 24 hrs. After that through visual inspection the stripping is determined. The stripping should be minimal possible

**3.4 Evaluation Of Properties Of The Bituminous Mix**

In the present study various tests were performed in the laboratory as per MORT&H, Nov-2000, Base & Surface course (Bituminous), Sec-500 and to examine the extent of segregation in the mixes and its effect on the properties. Initially the mix was tested for the binder content and then it's grading was obtained by sieve analysis. Then the mix was tested for various Marshall Strength parameters like density, stability, VFB, percent air voids and flow.

**3.4.1 Gradation of the Mix**

The various sieves used for the Sieve Analysis and their corresponding permissible percent passing as specified by the MOST are listed in the given table 3.1

Sieve size (mm)	Percentage passing
26.5	100
19	100
13.2	79-100
9.5	70-88
4.75	53-71
2.36	42-58
1.18	34-48
600 micron	26-38

Table 3.1 Specified Aggregate Gradation for (BC)

**3.4.2 Marshall method of Bituminous Mix Design.**

Bituminous mix design was carried out as per Highway Engineering by L.R. Kadyali. And MS-2, Mix Design Methods for Asphalt Concrete and Hot Mix Type.

Thickness of Compacted Layer, mm		40
Marshall Method Design Criteria		
I	Number of blows on each face	75
li	Marshall Stability, minimum (kg)	900
lii	Marshall Flow, mm	2-4
Iv	Voids in Compacted Mix, Va %	3-5
V	Voids Filled with Bitumen VFB,	65-75
Vi	Voids in Mineral aggregate VMA,	10-12 %

**Table 3.2: Design criteria for the various Marshall Strength Parameters**

**3.5 Fatigue Test by Repetitive Loading**

This test was conducted as per Beam fatigue equipment manual. The WFI Beam Fatigue Apparatus comprises cradle with pneumatic lateral positioning and servo-motor controlled vertical clamping. In this, the stand- alone version, the cradle has a digital servo-controlled pneumatic actuator built into the beam.

**3.5.1 The Beam Cradle**



The beam cradle has been designed to subject an asphalt beam specimen to 4 point bending with free rotation and horizontal & translation of all load and reaction points as shown in photograph. 3.10. The spacing between loading points can be either 300 mm or 355.5

**3.1:Fatigue beam apparatus**



**3.2 Compaction of beam 3.3. Fatiuge bam**

**3.5.2 Operator Control**

These controls are used to locate & clamp the specimen and position the actuator ram prior to starting a test and releasing the specimen at the completion of the test.



**3.4 Beam in testing position 3.5 Crack after testing beam**

**3.6WHEEL TRACKING TEST.**

This test was done as per Wheel tracking equipment manual.

**3.6.1Equipment and Procedure**

Rutting potential is key factor for design of various wearing bituminous surfaces. Rutting characteristics of BC, SDBC and SMA mixes were investigated using Wheel Tracking (Dry Type) equipment (HWTD). The Wheel tracker is capable of carrying out tests in accordance with British standard BS 598-part 10: 1998. The distance of travel (230+/- 5mm), rate of tracking (42 passes per minute) and wheel/tyre specifications are as detailed in BS 598. A typical view of test in progress

The specimen (slabs) were prepared and placed in the testing assembly at 45°C. The test was started after placing the specimen in closed cabinet as per test requirement. Each sample is subjected to reciprocating load (525±5 N) repetitions for 20,000 passes or until 20 mm rut impressions on the slab surface whichever is earlier




**Photograph 3.5: Wheel Tracking Test in Progress.**



**Photograph 3.6 : Mould of Rutting Slab**



**Photograph 3.7: Rutting Slab**



**Photograph 3.8 A Position of Beam after rutting test**

**4. LABORATORY INVESTIGATION & RESULTS**

**4.1 Physical properties of Aggregates & Bitumen**

In this chapter the results of various tests conducted in the laboratory are listed. The various properties of course aggregates and Bitumen

Sr. No.	Name of the property	Value in %
1	Aggregate Impact Value	15
2	Flakiness Elongation Index	22
3	Water absorption	1.0
4	Soundness test	3.5%
5	Loss Angeles abrasion test	16%

**Table 4.1: Physical properties of Aggregate.**

Sr. No	Bitumen Sample	Specific Gravity	Softening point °C	Ductility cm	Pene traction
1	60/70	1.01	47.7	74	65
2	PMB 40	1.02	67	>70	42
3	PMB 70	1.03	60	>90	70

**Table 4.2: Various properties of the Binder**

The specific gravity of coarse aggregate 20 mm, 13.2 mm, stone dust and lime are 2.67, 2.67, 2.69 and 2.80 respectively. Specific gravity of bitumen has been taken as 1.02

**4.2 Gradation of aggregate**


For the different sizes of aggregates, individual aggregates gradation has been done .To get the specified gradation of BC mix, aggregates of different sizes were blended with different proportion and many trials were made.

Sieve size (mm)	% Passing 12.5 mm	% Passing 6 mm	% Passing Stone dust	% Passing Lime	A: B: C: D - 28:32:37:3
	(A)	(B)	(C)	(D)	
19	100	100	100	100	100
13.2	89.1	100	100	100	97

9.5	38.5	100	100	100	82.8
4.75	6.33	66.3	99.7	100	62.9
2.36	2.78	32.7	92.9	100	48.6
1.18	0	11.56	84.7	100	38
600 μ	0	4.59	66.5	100	29.1
300 μ	0	2.07	48.7	100	21.7
150 μ	0	0	31.8	98.9	15
75 μ	0	0	10.4	80.3	6.3

Table 4.3: Prescribed limits as per MOST specifications

Fabric Type	Thick-ness (mm)	Asphalt Retention (kg/Sq. m)	Tensile strength (kg)	Melting Point Deg. Cel.	Mass per Area Gm/Sq. M
		-0.6	36	165	
Sample					140
M1	0.7	0.7	43	>150	145
N.S.W.B					
Sample M 2	1	1.6	46	>150	146
W.N.P 1					
Sample M 3	1.2	1.7	48	>150	145
W.N.P 2					



4.3 Identifications of Geosynthetic Material

Four different types' Geogride samples were purchased from the market for use

Table 4.4 Identification of Geosynthetic Material  
N. W. S. B. – Non- Woven Span Bund.  
W. N. P.- Woven Needle Punch.


4.4 Beam Fatigue Test

Beam fatigue test was done to find out fatigue life cycles of beams In this test constant strain method is use. As per standard the no. of cycle is more compared to other beam. With using every material 3 sample S1, S2, S3 taken.

Beam Details	No. of Cycles		
	100μ Strain	300μ Strain	500μ Strain
M1-S1 (60/70)	239700	-	-
M1-S2 (60/70)	-	219900	-
M1-S3 (60/70)	-	-	164000
M2-S1 (60/70)	383000	-	-
M2-S2 (60/70)	-	311800	-
M2-S3 (60/70)	-	-	221500
M3-S1 (60/70)	294000	-	-
M3-S2 (60/70)	-	231500	-
M3-S3 (60/70)	-	-	197000
Plain 1 (60/70)	229400	-	-
Plain 2 (60/70)	-	188700	-
Plain 3 (60/70)	-	-	117100
Plain 1 (PMB 40)	364400	-	-
Plain 2 (PMB 40)	-	307300	-


Plain 3 (PMB 40)	-	-	254200
Plain 1 (PMB 70)	411900	-	-
Plain 2 (PMB 70)	-	369000	-
Plain 3 (PMB 70)	-	-	277800

Table 4.5 Beam fatigue test Result




4.6 Wheel tracking test

This test is done to determine the rutting resistance of bituminous mixes. Wheel tracking tests were conducted on beam specimen prepared of bituminous mixes with asphalt coated Geotextile as an intralayer as well as 2/3 distance to the bottom face. The test has been done for 20000 passes Or 20 mm rutting, whichever earlier, and the rut depth was measured at interval of 2 hours.



Cycle	Slab M1 (T.G.U-40)	Slab M2 (T.G.U-60)	Slab M3 (T.G.U-100)	Plain Slab (60/70)
	1000	2.19	1.63	
2000	4.42	2.6	2.05	12.8
3000	5.81	3.49	2.84	13.26
4000	6.9	4.07	3.59	13.94
5000	8.02	4.57	4.15	14.19
6000	8.74	5.18	4.85	14.78
7000	9.23	5.55	5.04	15.44
8000	10.21	5.97	5.23	16.51
9000	10.41	6.02	5.41	17.4
10000	10.93	6.83	5.45	18.4
11000	11.32	6.99	6.02	19.15
12000	11.63	7.59	6.14	19.81
13000	11.98	7.96	6.71	20.46
14000	12.52	8.19	6.99	
15000	13.11	8.83	7.31	
16000	13.98	9.42	7.65	
17000	15.03	10.89	8.39	
18000	15.56	11.51	9.09	
19000	15.97	12.67	9.71	
20000	16.34	13.92	10.8	

Table 4.6 Rut depth of Bituminous mixes. (G.M. as intralayer)



Cycle	Slab M1 (T.G.U- 40)	Slab M2 (T.G.U -60)	Slab M3 (T.G.U -100)	Plain Slab (60/70)
1000	1.17	0.99	1.98	10.05
2000	2.21	2.14	3.76	11.3
3000	3.15	2.74	4.95	12.2
4000	3.89	3.2	6.05	13.01
5000	4.4	3.51	7.3	13.969
6000	5.01	3.82	7.99	14.18
7000	5.35	4.19	8.55	15.34
8000	5.63	4.66	9.61	15.99
9000	6	4.9	10.1	16.4
10000	6.44	5.15	10.33	17.95
11000	6.87	5.76	11	19.19
12000	7.75	6.02	11.21	19.96
13000	8.61	6.31	11.62	20.53
14000	9.07	6.64	11.97	
15000	9.98	7.21	12.27	
16000	10.67	7.55	12.81	
17000	11.22	8.25	13.44	
18000	11.78	8.67	13.91	
19000	12.31	9.01	14.4	
20000	12.65	9.37	14.87	

**Table 4.7 Rut depth of Bituminous mixes. (G.M. 2/3 depth of bottom)**

**5. COST-ECONOMICS**

The cost comparison per Km for 75 mm BC Mix using with using Geogride M1(T.G.U-40),M2(T.G.U-60),M3(TGU-100) respectively is shown below;

Assume,

Road length =1 km

Road width = 7 m. B.C. laying having thick =7.5 cm

- Total volume of bituminous Mix =  $1000 \times 7 \times 0.075 = 525 \text{ M}^3$
- Co Cost of bitumen = 40 Rs/ liter t of bitumen = 40
- Average assuming CDM =  $2420 \text{ kg/ M}^3$
- So, Total weight of mix/ km =  $2420 \times 525 = 12,70,500 \text{ kg}$ .
- Total loose weight of mix / km = 16,51,650 kg.
- Cost of bitumen per km =  $16,51,650 \times 4.45 \times 40 / 100 = 29,39,937 \text{ Rs/ Km}$
- Cost of road per km =  $29,39,937 \times 2.2 = 64,67,861 \text{ Rs/ Km}$  -----(1)

Area of road =  $1000 \times 7 = 7000 \text{ Sq.m}$

- If use Geogrid M1 (TGU-40), then cost is 60 Rs./ Sq. m including installation charges. Cost of Geogrid = 4, 20, 000 Rs. -----(2)
- If use Geogrid M1 (TGU-60), then cost is 90 Rs./ Sq. m including installation charges. Cost of Geogrid = 6, 30, 000 Rs. -----(3)
- If use Geogrid no-6 (TGU-100), then cost is 125 Rs./ Sq. m including installation charges. Cost of Geogrid = 8, 75, 000 Rs. -----(4)
- Apply a tack coat at the rate of 0.3 Kg / Sq. m
- Quantity of tack coat =  $7000 \times 0.3 = 2100 \text{ Kg}$ .
- Cost of tack coat including charges = 50 Rs.

- Cost of tack coat per Km. =  $2100 \times 50 = 1,05,000 \text{ Rs.-- (5)}$
- If use of Geogrid M1 (TGU-40) in construction of road, the cost will be summation of (1),(2) and (5); which is Rs.69,92,861 RS.
- If use of Geogrid M2 (TGU-60) in construction of road, the cost will be summation of (1),(3) and (5); which is Rs.72,02,861 RS.
- If use of Geogrid M3 (TGU-100) in construction of road, the cost will be summation of (1), (4) and (5); which is 74,47,861 Rs.
- Increase a cost 5, 25, 00 Rs,7,35,00 Rs & 11, 27, 000 Rs. If use Geogrid M1(TGU-40),M2(TGU-60)M3(TGU-100) Respectively, with reference of plain Bituminous concrete road.
- But, past experiment says if use Geogrid material then life of road will be increase up to 70 % means maintenance period increase.

**6. CONCLUSION**

The following conclusions were drawn based on Geogrid material in bituminous concrete mix to retard reflective cracking in bituminous overlays.

- Geogrid M1(TGU-40),M2(TGU-60)&M3(TGU100) has adequate tensile strength 64,105&146 kgs respectively.
- In beam fatigue test a no. of cycle required for particular strain value, Geogrid material of M1(TGU-40), M2 (TGU-60) & M3 (TGU-100) with 60/70 grade of bitumen is almost same of PMB-40 and PMB-70, so that if use of Geogrid material is beneficial in terms of economy.
- The no. of cycle for required strain value is high i.e. 2, 64,000& 2,81,500 & 2, 97, 000 for Geogrid material M1(TGU-40) & M2(TGU-60) & M3(TGU-100), when use Geogrid material as compared to plain beam i.e. 1,17,000.
- Geogrid material if placed at 2/3rd height from the bottom also increases the fatigue life but it may not be beneficial as it lies in the compression face of the beam.
- When Geogrid material M1(TGU-40) & M2(TGU-60) & M3(TGU-100) is provided at intralayer, rutting depth is decrease 11.92 mm,7.96 mm and 6.71 mm respectively as compared to plain slab.
- When Geogrid M1(TGU-40)&M2(TGU-60)&M3(TGU-100) is provided at 2/3 depth to bottom, rutting depth is decrease 11.62 mm ,8.61 and 6.31 mm respectively as compared to plain slab.
- The rutting of the bituminous overlay improves when the Geogrid material is placed nearer to the bottom surface.
- Finally it is concluded that it is more economical and feasible to use Geogrid material M1(TGU-40)&M2(TGU-60) & M3(TGU-100) as an intralayer.

**ACKNOWLEDGEMENTS**

This acknowledgment gives me an opportunity to show my gratitude for the people who stood by my side during whole task of dissertation. First and foremost I like to offer my gratitude to "Almighty God" to send me his blessings, inspirations, moral supports and to give me an opportunity to reach up to this level. First of all, I would like to indicate my deep gratitude to MR.SANJAY PATEL, my guide, for his inspiring and motivating guidance throughout the M.E Programme which will definitely enlighten in my life ahead. This paper presentation would never have been completed without his support, helpful comments, insightful suggestions and criticisms at the various stages, in addition to the generously spent time in reviewing this paper presentation.

I would like thank all the other teaching faculties of Transportation Engineering Department Shri M.R.Bhatt, Dr. P.J.Gundaliya, Shri Nikhil Raval sir for their stimulating supports in various ways.

**REFERENCE**

[1]. S.K. Palit, Y. CH. Srinivasa Reddy & PROF. B.B.Pandey, Reflective Cracking of Bituminous Overlays- A Laboratory Investigation, INDIAN HIGHWAYS Vol. 31 No 5 P 5- 14. | [2] T.Brooker,M.D Foulkes and C.K. Kennedy , Influence of Mix Design on Reflection Cracking Growth Rates through Asphalt Surfacing, of Asphalt PavementsVol- 1. | [3]. MS-2, Mix Design for Asphalt Concrete & Hot Mix Type. | [4]. MORT&H Section: 500 (2002), Specifications for Roads and Bridges | [5]. Beam fatigue equipment manual. | [6]. Wheel tracking equipment manual.