



## COMPARITIVE STUDY OF LIGHT CURE DRESSING AND NON - EUGENOL DRESSING AFTER PERIODONTAL FLAP SURGERY

### Dental Science

**Dr. Mahesh G. Chavda**

Professor Govt. Dental College Ahmedabad

**Dr. Neeta V. Bhavsar**

Professor & HOD Govt. Dental College Ahmedabad

**Dr. Mahendra Kumar Singh\***

3<sup>rd</sup> Year Post Graduate Student ) – Govt. Dental College Ahmedabad \*Corresponding Author

### ABSTRACT

**Aim-** Periodontal dressings have been used for protection of the surgical site. This study was designed to compare the clinical efficacy of light cured periodontal dressing (Barricaid) with non-eugenol periodontal dressing (Coe-Pak) following conventional flap surgery. **Methods-** Ten chronic periodontitis subjects requiring flap surgery on contralateral sides of the arch were selected and divided randomly into Site-A (Coe-Pak) and Site-B (Barricaid) on the basis of dressing placed post operatively. Parameters recorded were plaque index, plaque beneath dressing and questionnaire on preferred dressing material. **Results-** Site-B showed better results when scores of plaque index, plaque beneath dressing were compared, as the differences were statistically significant ( $P>0.05$ ). A significant number of subjects found Coe-Pak to have an unpleasant appearance and thus preferred Barricaid. **Conclusion-** Barricaid showed better patient acceptability and proved to be a good alternative to Coe-Pak periodontal dressing.

### KEYWORDS

Periodontal dressing , Light cure dressing , Barricaid , Periodontal flap surgery

### INTRODUCTION

Periodontal surgery involves the surgical manipulation of the oral mucosa and the tooth supporting structures to alleviate a variety of problems. However its sequelae are pain, swelling, inflammation, bleeding. Hence, most periodontists advocate that some form of protection should be applied over the surgically traumatized tissue so that it is shielded from further insult.<sup>1</sup>

Periodontal dressings were first introduced in 1923 when Dr. A.W.Ward advocated use of dressing material around the necks of the teeth and adjacent tissue, to cover and protect the wound after periodontal surgery. They are applied to serve as a bandage over the surgical site with the objective of holding the flap in place; protecting newly formed tissue; minimizing postoperative pain, infection and haemorrhage; protecting the surgical site from trauma during eating and drinking and finally, supporting mobile teeth during the healing process.<sup>2</sup> Periodontal dressings are generally grouped into three categories: (i) those containing zinc oxide and eugenol, (ii) those containing zinc oxide without eugenol and (iii) those containing neither zinc oxide nor eugenol. Due to the various side-effects of eugenol, latest periodontal dressings are usually formulated without it.<sup>3</sup>

A very widely used periodontal dressing is the non-eugenol dressing "Coe-Pak" (GC AMERICA, INC. ALSIP, IL 60803 U.S.A.), which offers a standard, to which other periodontal dressings can be compared. Although widely accepted, Coe-pak has a number of disadvantages, e.g., poor appearance, ill-defined setting time, poor flow properties during manipulation and poor adherence to mucosal surfaces.<sup>4</sup> Recently developed visible light-cured periodontal dressing material based on a polyether urethane dimethacrylate resin is stated to be an advanced concept in the protection of periodontal wound sites.<sup>5</sup> Commercially known as Barricaid (Dentsply International Inc. Milford, DE 19963-0359, U.S.A.), its superior physical properties like easy manipulation, better surface smoothness, interdental retention and mechanical stability favor its clinical application. Additionally, it possesses a translucent pink colour, which is esthetically pleasing. The aim of the present study was to compare the clinical efficacy of light-cured periodontal dressing (Barricaid) with noneugenol periodontal dressing (Coe-Pak) following conventional flap surgery.

### MATERIALS AND METHOD

The study design and protocol were approved by the Institutional ethical Board.

#### Study design

From the OPD, Department of Periodontology, Government Dental College Ahmedabad ten subjects with chronic periodontitis requiring conventional flap surgery on contralateral sides of the arch, were selected. On the basis of periodontal dressing that was to be placed post-operatively, the sides were divided into Site-A (Coe-Pak) and Site-B (Barricaid).

The inclusion criteria were- age group of 30-55 years of either sex, systemically healthy and cooperative subjects showing acceptable oral hygiene during phase-I therapy and similar periodontal involvement bilaterally as determined by clinical and radiographic assessment.

The exclusion criteria were- smokers and tobacco chewers, subjects on antibiotics or anti-inflammatory drugs in past 3 months, those with history of any gingival and/ or periodontal surgical treatment in past 6 months and subjects allergic to polyacrylic acid.

A detailed case history of the subjects participating in the study was recorded. Signed informed consent was taken prior to the study. Oral hygiene instructions were given and Phase-I therapy was completed for all the subjects.

#### Assessment of clinical parameters

The Plaque Index (Silness and Loe 1964) were recorded at baseline (pre-operative) and one week post-operatively. Plaque underneath dressing (modification of debris index by Greene and Vermilion) evaluated after removal of dressing.<sup>6</sup> All these parameters were recorded by a single examiner who was blinded for the surgical procedures and pack applications. In addition, patients were also given a post-operative assessment questionnaire in which they were asked about taste, appearance, and retention of both the dressings and following the second procedure, they were requested to state their preference, if any, for a particular dressing.

#### Surgical procedure

Periodontal flap surgery was performed under local anaesthesia, following aseptic techniques. At Site-A, following sulcular incisions, a full thickness mucoperiosteal flap was reflected both facially and lingually. After thorough debridement and root planing of the exposed root surface, the flap was placed in its original position and sutured using non-resorbable silk sutures. The surgical site was dried using gauze, and Coe-Pak was then applied.

The photocured dressing was dispensed at the juncture of the cervical one-third of the teeth and the margin of the surgical site on the facial aspect. It was exposed to a visible light-curing unit for 10 seconds per

site per tooth until the entire dressing was cured. Same procedure was repeated for the lingual side. All the surgical procedures were carried out by the same operator. The dressings were removed after seven days.

All the data obtained was statistically analysed. Descriptive statistics were expressed as mean  $\pm$  standard deviation (SD) for each group. The change in mean scores of Plaque Index over a period of 1 week in each group was analysed using Paired-t test. Intergroup comparison was done using Unpaired-t test. The post-operative assessment variables were analysed using questionnaire format. In the above tests, p value less than or equal to 0.05 ( $P \leq 0.05$ ) was taken to be statistically significant. All analyses were performed using SPSS software version 17.

## FIGURES



Figure 1: Coe pak dressing (Site A) & Barricaid dressing (Site B)



Figure 3 : Barricaid dressing removed from buccal surfaces of teeth and immersed in plaque disclosing solution. Amount of plaque can be visualized on inner aspect of removed dressings

## RESULTS

### Plaque index

At Site-A and Site-B, the mean increase in Plaque index scores from baseline to day 7 were  $1.08 \pm 0.25$  and  $0.73 \pm 0.28$  respectively, which was statistically significant ( $P < 0.001$ ). On comparison, the change in score at Site-B was significantly lesser than Site-A.

Table 1: Change in Plaque index score at Site A & B

| Plaque Index Score      | Site A (Coe Pak)<br>Mean $\pm$ SD | Site B (Barricaid)<br>Mean $\pm$ SD | Unpaired t test<br>(p value) |
|-------------------------|-----------------------------------|-------------------------------------|------------------------------|
| Baseline                | $0.82 \pm 0.31$                   | $0.77 \pm 0.21$                     | 0.68                         |
| After 7 days            | $1.90 \pm 0.21$                   | $1.50 \pm 0.66$                     | 0.08                         |
| Change in Mean(0-7)     | $1.08 \pm 0.10$                   | $0.73 \pm 0.45$                     |                              |
| Paired t test (p value) | < 0.001                           | 0.005                               |                              |

This was the most significant finding in the present study. It was evaluated on the 7th day according to modified Greene and Vermillion's criteria. Site A showed a greater amount of plaque accumulation under dressings as compared to Site B

Table 2 Comparison of mean values of plaque underneath dressing

| Plaque underneath dressing | (Mean $\pm$ SD) | P value |
|----------------------------|-----------------|---------|
| Site A                     | $2.75 \pm 0.26$ | < 0.001 |
| Site B                     | $2.20 \pm 0.34$ |         |

Table 3 : Table depicting assessment of the dressings by the subjects in Site A and Site B

| Subject's assessment   | Site A | Site B |
|------------------------|--------|--------|
| Loose dressings        | 6      | 2      |
| Unpleasant appearance  | 8      | 1      |
| Unpleasant taste/smell | 7      | 2      |

|                                  |   |   |
|----------------------------------|---|---|
| Irritation / Burning sensation   | 3 | 4 |
| Difficulty in speech/mastication | 5 | 2 |
| Preferred dressing               | 3 | 7 |

## DISCUSSION

Use of dressing materials in periodontics has remained debatable. Various schools of thought have their own reasoning and claims. Authors such as Wikesjo et al., Sigusch et al supports the use of dressing materials whereas others such as Loe and Silness, Stahl et al. do not favour the use of periodontal dressing material.<sup>7</sup> However, one of the most widely used non-eugenol dressings is Coe-Pak. When new dressing materials with claims of superior properties are developed, their clinical performance should be assessed and compared with established products.<sup>4</sup>

In this study, a greater number of subjects preferred Barricaid as a post-operative periodontal dressing over Coe-Pak. The results of this study are in accordance with those of other studies that have been carried out earlier.

Application of dressing has been said to be associated with more plaque accumulation. The results for plaque index showed a significant increase in the scores at both sites- A and B after 1 week. These results are in accordance with the study of Heaney and Appleton (1976)<sup>8</sup>, Pluss et al (1975)<sup>9</sup>, Newman and Addy (1982)<sup>10</sup>, Sachs et al (1984)<sup>11</sup> who reported accumulation of plaque beneath the periodontal dressings but not to a detrimental level to retard the healing process.

Further, studies done by Alpar B et al (1999)<sup>7</sup> showed that Barricaid did not inhibit growth of human primary gingival fibroblasts, while Coe-Pak reduced their proliferation. Schmalz G and Bindeslev AD (2009)<sup>12</sup> found that light-cured periodontal dressings were not cytotoxic in cell cultures and different cell types. Madan E et al (2013)<sup>13</sup> in their study concluded that Barricaid is easily applied and offers a perfect colour match; hence the patient is not hesitant to carry out his routine activities. With due consideration to the above, it is important to emphasize that a larger sample size needs to be taken up to compare the efficacy of these two periodontal dressings.

## CONCLUSION

The results of this study showed that visible light-cured periodontal dressing Barricaid had better patient acceptability and proved to be an esthetic alternative to conventional Coe-Pak as a dressing material. Thus it can be preferred over Coe-Pak for application in the anterior esthetic region following periodontal surgery.

## REFERENCES

- Fraunhofer JA, Argyropoulos DC. Properties of periodontal dressings. Dent Mater 1990; 6:51-5.
- Kathariya R, Jain H, Jadhav T. To pack or not to pack: the current status of periodontal dressings. J Appl Biomater Funct Mater 2015; 13(2):e73-e86.
- Rubinoff CH, Greener EH, Robinson PJ. Physical properties of periodontal dressing materials. J Oral Rehabil 1986; 13:575-86.
- Cheshire PD, Griffiths GS, Griffiths BM, Newman HN. Evaluation of the healing response following placement of Coe-pak and an experimental pack after periodontal flap surgery. J Clin Periodontol 1996; 23:188-93.
- Nalmas S, Prakash S, Mehta DS. Periodontal dressings in periodontal therapy – an update. J Ind Dent Assoc 2000; 71:74-179.
- Greene JC, Vermillion JR. The simplified oral hygiene index. J Am Dent Assoc 1964; 68:713.
- Alpar B, Gunay H, Geurtsen W, Leyhausen G. Cytocompatibility of periodontal dressing materials in fibroblast and primary human osteoblast like cultures. J Clinical oral investigations. 1999; 3(1):41-8.
- Heaney TG, Appleton J. The effect of periodontal dressings on healthy periodontium. J Clin Periodontol 1976; 3:66-76.
- Pluss EM, Engelbergler PR, Ratcheshank KH. Effect of chlorhexidine on dental plaque formation under periodontal pack. J Clin Periodontol 1975; 2:136-42.
- Newman PS, Addy M. Comparison of hypertonic saline and chlorhexidine mouth rinses after inverse bevel flap procedures. J Periodontol 1982; 53:315-8.
- Sachs HA, Farnoush A, Checchi L, Joseph CE. Current status of periodontal dressings. J Periodontol 1984; 55:689-96.
- Schmalz G, Arenholt-Bindslev D. Biocompatibility of dental materials. Berlin: Springer; 2009.
- Madan E, Bharti V, Chaubey KK, Arora VK, Thakur RK, Nirwal A. Light-cured resin "Barricaid" -An esthetic and biocompatible dressing: A step ahead. J Indian Soc Periodontol 2013; 17:753-6.